

Supporting Information

Iron Carbide Nanoplatelet: Colloidal Synthesis and Characterization

Frank M. Abel,^{*a} Shirin Pourmiri^a, Georgia Basina^b, Vasileios Tzitzios^{*,b,c}, Eamonn, Devlin^c, and George C. Hadjipanayis^a




Figure S1. Mössbauer spectroscopy performed at 4.2 K of sample synthesized at 300 °C for 1 hour followed 340 °C for 2 hours, showing a mixture of iron carbide phases and a small percentage of iron oxides.

^a Department of Physics and Astronomy, University of Delaware, Newark, DE 19716, USA.

^b Department of Chemical Engineering, Khalifa University of Science and Technology, Petroleum Institute, P.O. Box 2533, Abu Dhabi, United Arab Emirates.

^c Institute of Nanoscience and Nanotechnology, NCSR Demokritos, Athens, 15310, Greece

* Corresponding Authors: Frank M. Abel, E-mail: fabel@udel.edu, frank.m.abeliii@gmail.com, Vasileios Tzitzios, E-mail: v.tzitzios@inn.demokritos.gr