



Table S1 Zeta potential data of CdSe/ZnS@SiO₂ and CdSe/ZnS @SiO₂- NH₂

Sample	Potential Distribution	Zeta Potential (mV)
CdSe/ZnS @SiO ₂		-31.9 ± 4.1
CdSe/ZnS@SiO ₂ - NH ₂		-2.56 ± 3.3