

Self-cleaning and robust superhydrophobic CuO coating by jet-nebulizer spray pyrolysis technique

Sanjay S. Lathe,^a P.Sudhagar,^{a*} C. Ravidhas,^{b*} A. Jennifer christy,^b D. David Kirubakaran,^b R.Venkatesh,^b Anitha Devadoss,^a C. Terashima,^{a,c} K. Nakata^{a,c} and Akira Fujishima^{a,c}

S1. Contact angle

Table S1. Contact angles of different CuO coatings on glass substrates

Sample	Contact angle
CuO-10	130°
CuO-20	140°
CuO-30	154°
CuO-40	125°