

Supporting Information

Magnetic Two-dimensional Molecularly Imprinted Materials for Recognition and Separation of Proteins

Fangfang Chen, Weifeng Zhao, Jingjing Zhang and Jie Kong*

MOE Key Laboratory of Space Applied Physics and Chemistry, Shaanxi Key

Laboratory of Macromolecular Science and Technology, School of Science,

Northwestern Polytechnical University, Xi'an, 710072, P. R. China

*E-mail: kongjie@nwpu.edu.cn, Tel.(fax): +86-29-88431621

Table S1 Effect of BSA amount on the binding of BSA onto BSA 2D-MIPs^a

Content of template BSA (mg)	Adsorption capacity (Q, mg/g)
5	43.14±1.82
10	64.51±3.98
15	75.86±3.19
20	86.38±3.65
30	87.04±2.76

^aAmount of BSA 2D-MIPs was 20 mg; volume:1 mL; the concentration of BSA: 1 mg/mL; incubation time: 1 h at room temperature.