Electronic Supplementary Material (ESI) for Catalysis Science & Technology. This journal is © The Royal Society of Chemistry 2016

Electronic Supplementary Information (ESI)

for

The studies on the epoxidation of methallyl chloride over the TS-1 microsphere catalyst in the continuous slurry reactor

Zhixia Deng, Yulin Yang, Xinqing Lu, Jianghong Ding, Mingyuan He, Peng Wu*

Shanghai Key Laboratory of Green Chemistry and Chemical Processes, Schooll of Chemistry and Molecular Engining, East China Normal University, Shanghai 200062, China

E-mail: pwu@chem.ecnu.edu.cn (P. Wu)

Fax: +86-21 62232292

LIST OF TABLES:

Table S1. The ratio of Si/Ti for fresh, first regenerated, second regenerated, and thirdly regenerated TS-1-MS catalysts given by ICP.

LIST OF FIGURES:

Figure S1. UV-vis spectra of TS-1 (a) and TS-1-MS (b).

Figure S2. XRD patterns (A), UV-vis spectra (B) of fresh TS-1-MS (a), first regenerated (b), second regenerated (c), and thirdly regenerated (d).

Table S1 The ratio of Si/Ti for fresh, first regenerated, second regenerated, and thirdly regenerated TS-1-MS catalysts given by ICP.

Samples	fresh	first	second	thirdly
		regenerated	regenerated	regenerated
Si/Ti	40	41	41	42




Figure S1. UV-vis spectra of TS-1 (a) and TS-1-MS (b).




Figure S2. XRD patterns (A), UV-vis spectra (B) of fresh TS-1-MS (a), first regenerated (b), second regenerated (c), and thirdly regenerated (d).