

Supporting Information

Efficient Extraction of Sulfate from Water using a Metal-Organic Framework

Ashlee J. Howarth,^a Timothy C. Wang,^a Salih S. Al-Juaid,^a Saadullah G. Aziz,^a Joseph T. Hupp,^{*a} Omar K. Farha^{*ab}

^aDepartment of Chemistry, Northwestern University, 2145 Sheridan Road, Evanston, Illinois 60208-3113, United States

^bDepartment of Chemistry, Faculty of Science, King Abdulaziz University, Jeddah, Saudi Arabia




Figure S1. Langmuir plot (linear, type I) for sulfate adsorption on NU-1000.

Table S1. Values of C_e and q_e used in Figure S1 for sulfate adsorption on NU-1000.

Ca. Exposure per Node	C_e (ppm)	Q_e (mg/g)
1.0	5.5	37.1
1.5	8.8	46.5
2.0	18.8	47.0
2.5	25.8	47.7
3.0	39.0	53.1

Table S2. Sulfate adsorption per node in NU-1000 when exposed to various concentrations of aqueous sodium sulfate.

Exposure per Node	Uptake per Node
2	1.3
3	1.3
4	1.3
5	1.3
6	1.5
7	1.5

Table S3. Representative sulfate adsorption capacities for various sorbents including NU-1000.

Material	Sulfate Adsorption mg/g
Tripodal Hexaurea Receptor ¹	184
Tris[2-(3-pyridylurea)ethyl]-amine ²	81
NU-1000	56
Oligopyrrolic Macrocycle ³	52
Acrylic Acid Grafted Cotton ⁴	33
Zeotreat TM (modified mordenite) ⁵	5




Figure S2. Sulfate uptake as a function of time in the presence of 10-50x the molar concentration of NO_3^- .




Figure S3. Sulfate leaching from NU-1000 in the presence of 50x the molar concentration of NO_3^- vs. NO_3^- -free water as a control.




Figure S4. PXRD patterns for NU-1000 before and after adsorption of sulfate.




Figure S5. Nitrogen adsorption isotherms of NU-1000 before and after adsorption of sulfate.

References:

1. C. Jia, B. Wu, S. Li, X. Huang, Q. Zhao, Q.-S. Li, X.-J. Yang, *Angew. Chem. Int. Ed.* 2011, **50**, 486–490.
2. R. Custelcean, A. Bock, B. A. Moyer, *J. Am. Chem. Soc.* 2010, **132**, 7177–7185.
3. E. A. Katayev, J. L. Sessler, V. N. Khrustalev, Y. A. Ustynyuk, *J. Org. Chem.* 2007, **72**, 7244–7252.
4. H. H. Sokker, H. H. Sokker, *Journal of Nuclear Technology in Applied Science* 2014, **2**, 345–354.
5. C. Vidal, U. Broschek, G. Zuñiga, L. Bravo, International Mine Water Association. *Zeotreat: Multifunctional Adsorbents For Metal And Sulphate Removal In Mining Wastewaters From Copper Industry, Chilean Case*