

ARTICLE

Graphene oxide immobilized enzymes show high thermal and solvent stability

Cite this: DOI: 10.1039/x0xx00000x

Soňa Hermanová^a, Marie Zarevucká^b, Daniel Bouša^c, Martin Pumera^d and Zdeněk Sofer^{*,c}

Received 00th January 2012,

Accepted 00th January 2012

DOI: 10.1039/x0xx00000x

www.rsc.org/

SUPPORTING INFORMATION




Fig. SI 1 Zeta potential (mV) of graphene oxide as the function of the solution pH.

Table SI 1 Elemental analysis of graphene oxide supports.

Sample	Wt.% N	Wt.% C	Wt.% S	Wt.% H	Wt.% O
BR-GO	0.40	66.87	0.00	1.35	31.38
ST-GO	0.30	73.70	0.00	1.00	25.00