Sulfur poisoning of emergent and current electrocatalysts:

vulnerability of MoS₂, and direct correlation to Pt hydrogen

evolution reaction kinetics

Shu Min Tan^a, Zdenek Sofer^b, and Martin Pumera^{a,*}

 ^a School of Physical and Mathematical Science, Division of Chemistry and Biological Chemistry, Nanyang Technological University, 21 Nanyang Link, Singapore 637371.
pumera.research@gmail.com

^b Department of Inorganic Chemistry, University of Chemistry and Technology Prague,

Technická 5, 166 28 Prague 6, Czech Republic.



Figure S1. Survey scan XPS spectra of Pt/C (A) and MoS₂ (B) poisoned with increasing concentrations of NaHS, in which several prominent peaks were labelled. The concentrations of NaHS used are 0, 12.5, 25, 50, 100, 500 and 1000 mM, as indicated in the individual spectra.



Figure S2. (A) HER LSV curves of Pt/C and MoS_2 poisoned with increasing concentrations of NaHS. (B) Corresponding Tafel plots of curves in (A).

Table	S1.	Surface	atomic	compositions	of	Pt/C	and	MoS_2	quantified	from	wide	scan	XPS
spectra	ı.												

-		Pt/C		MoS ₂					
[NaHS]/mM	S2p	C1s	O1s	S2p	Mo3d	C1s	O1s		
0	1.41	63.27	6.60	2.78	0.86	73.34	4.92		
12.5	1.73	65.67	10.10	2.77	0.37	77.28	8.40		
25	2.98	67.07	14.12	7.78	0.80	65.00	15.17		
50	3.17	65.39	15.53	10.07	0.85	60.66	18.48		
100	3.24	65.98	13.82	8.07	0.46	63.81	21.33		
500	3.45	69.51	18.29	12.88	0.99	56.76	24.59		
1000	4.01	66.31	21.51	9.51	0.72	61.59	22.65		

atomic percentage (at.%)