


Supporting information

EDS analysis of porous carbon



El	AN	Series	unn. C	norm. C	Atom. C	Error
			[wt.%]	[wt.%]	[at.%]	[wt.%]

C	6	K-series	88.78	88.78	91.54	10.6
O	8	K-series	8.13	8.13	5.97	1.6
N	7	K-series	2.61	2.61	2.30	1.2
S	16	K-series	0.47	0.47	0.18	0.1

Total: 100.00 100.00 100.00