

## Surface ionic states and structure of titanate nanotubes

Sesha Vempati,<sup>a\*</sup> Fatma Kayaci,<sup>a,b</sup> Cagla Ozgit-Akgun,<sup>a,b</sup> Necmi Biyikli<sup>a,b</sup> and Tamer Uyar<sup>a,b\*</sup>

<sup>a</sup> UNAM-National Nanotechnology Research Center, Bilkent University, Ankara, 06800, Turkey.

E-mail: SV: svempati01@qub.ac.uk; TU: uyar@unam.bilkent.edu.tr

<sup>b</sup> Institute of Materials Science and Nanotechnology, Bilkent University, Ankara, 06800, Turkey


### Supplementary information

STab 1: Literature review of the preparation of zinc titanates.


Type of reaction	Compound(s)	Temp (°C)	Duration	Phase information/comment	Ref
Citrate method	Zinc titanate	720	12h	-	[1]
Sol-gel	<i>c</i> -ZnTiO <sub>3</sub>	700	5h	Rh-ZnTiO <sub>3</sub>	[2]
	ZnTiO <sub>3</sub>	700	2h	Amorphous-ZnTiO <sub>3</sub> , Zn <sub>2</sub> TiO <sub>4</sub> , R-TiO <sub>2</sub>	[3]
	Crystalline-ZnTiO <sub>3</sub>	900	2h	Zn <sub>2</sub> TiO <sub>4</sub> , R-TiO <sub>2</sub>	[3]
	<i>h</i> -ZnTiO <sub>3</sub>	800	NA	Zn <sub>2</sub> TiO <sub>4</sub> , R-TiO <sub>2</sub>	[4]
	nanocrystalline ZnTiO <sub>3</sub>	400		Amorphous	[5]
	<i>c</i> -ZnTiO <sub>3</sub>	800	3h	R-TiO <sub>2</sub> , Zn <sub>2</sub> TiO <sub>4</sub> : 27.4, 42.7°	[5]
	<i>c</i> -ZnTiO <sub>3</sub>	900 W, μ-wave heating	10 min	Broad and low intensity peaks oriented in (311) plane	[5]
	Rh-ZnTiO <sub>3</sub>	500	1h	<i>c</i> -ZnO, <i>c</i> -Zn <sub>2</sub> TiO <sub>4</sub>	[6]
Sol-gel/Pechini	ZnTiO <sub>3</sub>	800	6h	Zn <sub>2</sub> TiO <sub>4</sub> , R-TiO <sub>2</sub>	[7]
Pechini	ZnTiO <sub>3</sub>	800	6h	R-TiO <sub>2</sub> , Zn <sub>2</sub> TiO <sub>4</sub>	[8]
High energy ball milling	ZnTiO <sub>3</sub> , Zn <sub>2</sub> TiO <sub>4</sub>	-	3h	-	[9]
	ZnTiO <sub>3</sub> , Zn <sub>2</sub> TiO <sub>4</sub>	-	6h	R-TiO <sub>2</sub>	[9]
Solid-state	Perovskite ZnTiO <sub>3</sub>	800	12h	Zn <sub>2</sub> TiO <sub>4</sub> , R-TiO <sub>2</sub>	[10]
Co-precipitation	Zinc titanate	700	2h	Secondary phases	[11]

#### References

- [1] Chem. Eng. Sci., 1992, **47**, 1421–1431  
 [2] J. Mater. Sci. Lett., 2001, **20**, 573–575  
 [3] J. Sol-Gel Sci. Technol., 2005, **33**, 103–106  
 [4] Mater. Lett., 2005, **59**, 197–200  
 [5] J. Phys. Chem. Solids, 2007, **68**, 317–323  
 [6] J. Euro. Ceram. Soc., 2010, **30**, 947–961  
 [7] J. Cryst. Growth, 2002, **243**, 319–326  
 [8] Mater. Res. Bull., 2008, **43**, 1066–1073  
 [9] Physica E, 2006, **33**, 69–76  
 [10] Ceram. Int., 2004, **30**, 2183–2189  
 [11] Ind. Eng. Chem. Res., 1998, **37**, 1929–1933  
*c*-cubic; Rh-Rhombohedral; R-rutile;



SFig 1: (a) diameter and (b) length of the grains observed for ZT14 after calcination.



SFig 2: X-ray photoelectron spectra depicting survey of elements. The atomic percentages are shown on the image for the three compounds.