

BrNi-0.0

Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 1

Standard :

O SiO₂ 1-Jun-1999 12:00 AM

Na Albite 1-Jun-1999 12:00 AM



Si SiO₂ 1-Jun-1999 12:00 AM

Ni Ni 1-Jun-1999 12:00 AM

Zr Zr 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	35.61	68.15
Na K	2.36	3.14
Si K	9.21	10.04
Ni L	5.06	2.64
Zr L	47.76	16.03
Totals	100.00	

Comment:



Spectrum processing :

No peaks omitted



Processing option : All elements analyzed (Normalised)

Number of iterations = 1

Standard :

O SiO2 1-Jun-1999 12:00 AM
 Na Albite 1-Jun-1999 12:00 AM
 Si SiO2 1-Jun-1999 12:00 AM
 Ni Ni 1-Jun-1999 12:00 AM
 Zr Zr 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	38.62	70.51
Na K	2.38	3.03
Si K	9.30	9.68
Ni L	4.93	2.45
Zr L	44.77	14.34
Totals	100.00	



Comment:

Spectrum processing :

No peaks omitted



Processing option : All elements analyzed (Normalised)

Number of iterations = 1

Standard :

O SiO2 1-Jun-1999 12:00 AM
 Na Albite 1-Jun-1999 12:00 AM
 Si SiO2 1-Jun-1999 12:00 AM
 Ni Ni 1-Jun-1999 12:00 AM
 Zr Zr 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	39.14	70.80
Na K	2.78	3.50
Si K	8.88	9.15
Ni L	5.36	2.64
Zr L	43.84	13.91
Totals	100.00	



Comment: