

ELECTRONIC SUPPLEMENTARY INFORMATION


Small molecule-based photocrosslinkable fluorescent materials toward multilayered and high-resolution emissive patterning

Simon Olivier,^{a,b} Lionel Derue,^c Bernard Geffroy,^c Tony Maindron,^b Eléna Ishow^{*a}

^aCEISAM–UMR CNRS 6230, Université de Nantes, 2 rue de la Houssinière, 44322 Nantes, France. ^bCEA LETI, LETI/DOPT/SCOOP/LCV, Minatech Campus, 17 rue des Martyrs, 38054 Grenoble, France. ^cCEA Saclay, IRAMIS (UMR CNRS 3685), LICSEN, F-91191 Gif-sur-Yvette, France. LPICM-UMR CNRS 7647, Ecole Polytechnique, Route de Saclay, 91128 Palaiseau, France.

CONTENT

1. Differential Scanning Calorimetry thermograms







Figure S1. DSC thermograms for compounds **7** and **8** on the [-30; 140] °C temperature range using a 30 °C.min⁻¹ thermal gradient.

2. AFM imaging of stacked photopatterns






Figure S2. AFM images of thin films **7** (a) and **8** (b) containing 3 mol. % TPO before irradiation, after irradiation ($\lambda_{\text{exc}} = 365 \text{ nm}$ with a 6.3 J.cm^{-2} exposure dose), and after development. A) Phase contrast, and B) topography images.




Figure S3 AFM images of a stacked bilayer obtained after successive deposition, photoirradiation and development of solution of red emitter **8** and green emitter **7** containing 3 mol. % TPO ($\lambda_{\text{exc}} = 365 \text{ nm}$ with a $0.026 \text{ J.cm}^{-2}.\text{cm}^{-2}$ exposure dose).