

Supplemental Information

Characterization of TLR4/MD-2-modified Au sensor surfaces. Towards the detection of molecular signatures of bacteria.

Kaveh Amini¹, Iraklili I. Ebralidze¹, Nora W.C. Chan², Heinz-Bernhard Kraatz¹ *

¹Department of Physical and Environmental Sciences, University of Toronto
Scarborough, Toronto, ON, Canada

²Defence Research and Development Canada - Suffield Research Centre
PO Box 4000 Station Main, Medicine Hat, Alberta, T1A 8K6, Canada

* Corresponding author email: bernie.kraatz@utoronto.ca; fax: (+1) 416-287-7279




Fig. S 1 Investigation of the electrochemical behaviour of the Lip-NHS modified Au electrode LPS (*E. coli*). (A) Shows the R_{ct} value obtained for incubation in the absence of LPS and has been provided for comparison and (B) show the R_{ct} values for incubation at different concentrations of LPS




Fig. S 2 Au 4d XPS signals for bare Au, TLR4/MD-2-modified Au and LPS/TLR4-MD-2-modified Au. The attenuation of these Au 4d signals have been used for estimating the overlayer thicknesses.

Table S1 Equivalent circuit element values for TLR4/MD-2-modified electrodes after incubation in LPS from *E. coli* solutions at different concentrations. Values in parentheses represent the standard deviation for at least 5 electrode measurements.

Equivalent Circuit elements (LPS <i>E.coli</i>)							
LPS Concentration (EUmL ⁻¹)	R _s (Ω·cm ²)	Capacitanc e (F/cm ²)	R _{dL} (Ω·cm ²)	CPE (F/s ^{1/2} ·cm ²)	n	R _{ct} (Ω·cm ²)	W (μF ^{1/2} cm ²)
0	0.8	1.4×10^{-5} (0.5)	1.4 (3.5 × 10 ⁻⁶)	5.2×10^{-5} (1.5 × 10 ⁻⁵)	0.8 (0.02)	250.8 (11.3)	0.02 (0.01)
	1.0	1.4×10^{-5} (0.6)	1.4 (5.6 × 10 ⁻⁶)	6.8×10^{-5} (9.5 × 10 ⁻⁶)	0.8 (0.01)	261.2 (22.3)	0.01 (0.01)
0.0005	0.6	1.8×10^{-5} (0.6)	1.4 (3.8 × 10 ⁻⁶)	9.0×10^{-5} (5.1 × 10 ⁻⁶)	0.8 (0.01)	375.6 (18.7)	0.02 (0.01)
	1.1	1.4×10^{-5} (0.8)	1.4 (8.6 × 10 ⁻⁶)	7.2×10^{-5} (6.9 × 10 ⁻⁶)	0.8 (0.01)	543.5 (24.3)	0.01 (0.02)
0.005	1.0	1.6×10^{-5} (0.5)	1.4 (4.6 × 10 ⁻⁶)	4.5×10^{-5} (7.6 × 10 ⁻⁶)	0.8 (0.01)	712.6 (29.1)	0.01 (0.01)
	1.5	1.3×10^{-5} (0.6)	1.5 (4.5 × 10 ⁻⁶)	4.5×10^{-5} (1.1 × 10 ⁻⁵)	0.8 (0.03)	960.3 (33.5)	0.02 (0.02)

Table S2 Equivalent circuit element values for TLR4/MD-2-modified electrodes after incubation in LPS from *Salmonella* solutions at different concentrations. Values in parentheses represent the standard deviation for at least 5 electrode measurements.

Equivalent Circuit elements (LPS (<i>Salmonella</i>))							
LPS Concentration (EUmL ⁻¹)	R _s (Ω·cm ²)	Capacitance (F/cm ²)	R _{dl} (Ω·cm ²)	CPE (F/s ^{1/2} ·cm ²)	n	R _{ct} (Ω·cm ²)	W (μF ^{1/2} cm ²)
0	0.7 (0.2)	9.9 × 10 ⁻⁶ (5.5 × 10 ⁻⁶)	1.8 (0.3)	1.7 × 10 ⁻⁵ (6.3 × 10 ⁻⁶)	0.8 (0.01)	261.8 (14.3)	0.01 (0.01)
0.0005	0.8 (0.2)	9.6 × 10 ⁻⁶ (4.2 × 10 ⁻⁶)	1.7 (0.1)	1.9 × 10 ⁻⁵ (4.5 × 10 ⁻⁶)	0.8 (0.01)	277.6 (31.3)	0.01 (0.01)
0.005	1.4 (0.8)	1.1 × 10 ⁻⁵ (8.8 × 10 ⁻⁶)	1.4 (0.1)	1.6 × 10 ⁻⁵ (2.1 × 10 ⁻⁶)	0.9 (0.02)	389.8 (28.7)	0.01 (0.01)
0.05	0.6 (0.5)	1.0 × 10 ⁻⁵ (5.3 × 10 ⁻⁶)	1.8 (0.2)	1.4 × 10 ⁻⁵ (3.9 × 10 ⁻⁶)	0.9 (0.01)	568.9 (22.4)	0.01 (0.02)
0.5	1.2 (0.4)	9.6 × 10 ⁻⁶ (3.9 × 10 ⁻⁶)	1.8 (0.1)	2.5 × 10 ⁻⁵ (6.3 × 10 ⁻⁶)	0.8 (0.02)	739.6 (26.8)	0.03 (0.01)
5	0.8 (0.7)	9.2 × 10 ⁻⁶ (3.5 × 10 ⁻⁶)	1.5 (0.2)	2.5 × 10 ⁻⁵ (4.6 × 10 ⁻⁶)	0.8 (0.02)	1002.3 (38.4)	0.01 (0.02)