

Electronic Supporting Information

Eco-fabrication of Hierarchical Porous Silica Monoliths by Ice-Templating of Rice Husk Ash

A. Bahrami^{a,b}, U. Simon^a, N. Soltani^{a,b}, S. Zavareh^a, J. Schmidt^c, M. I. Pech-Canul^b, A. Gurlo^a

^a*Fachgebiet Keramische Werkstoffe / Chair of Advanced Ceramic Materials, Institut für Werkstoffwissenschaften und -technologien, Technische Universität Berlin, Hardenbergstraße 40, 10623 Berlin, Germany.*

^b*Centro de Investigación y de Estudios Avanzados del IPN Unidad Saltillo, Ave. Industria Metalúrgica No. 1062, Parque Industrial Saltillo-Ramos Arizpe, Ramos Arizpe, Coahuila, México, 25900.*

^c*Fachgebiet Funktionsmaterialien, Institut für Chemie, Sekr. BA 2, Technische Universität Berlin, Hardenbergstr. 40, 10623, Berlin, Germany.*

Table ESI-1. Chemical composition (wt. %) and density of rice husk, ARHA and CRHA

	Fe_2O_3	Al_2O_3	Na_2O	K_2O	SO_3	P_2O_5	MgO	Other species	SiO_2	Density (g/cm ³)
RH	0.037	0.28	0.13	0.38	0.083	0.18	0.24	80.4	17.5	---
ARHA	0.0264	0.042	0.081	0.021	0.242	0.047	0.0691	0.902	98.57	1.60
CRHA	0.0359	0.078	0.236	0.321	0.112	0.317	0.297	2.474	96.45	2.57




Figure ESI-1. a) XRD pattern and b) Si-NMR of amorphous silica.




Figure ESI-2. XRD patterns of amorphous and crystalline rice husk ash (CRHA) after heat-treatment at under air for 2 hours.