

Supporting Information

Mesoporous carbon confined palladium-copper alloy composites for high performance nitrogen selective nitrate reduction electrocatalysis

Jianwei Fan,^{*a} Huawei Xu,^a Menghua Lv,^a Jinxiu Wang,^c Wei Teng,^a Xianqiang Ran,^a Xiao Gou,^a Xiaomin Wang,^a Yu Sun^d and Jianping Yang^{*a,b}

^a College of Environmental Science and Engineering, State Key Laboratory of Pollution Control and Resources Reuse, Tongji University, Shanghai 200092, P. R. China

^b State Key Laboratory for Modification of Chemical Fibers and Polymer Materials, College of Materials Science and Engineering, Donghua University, Shanghai 201620, P. R. China.

^c Department of Chemistry and Laboratory of Advanced Materials, Fudan University, Shanghai 200433, P. R. China

^d Shanghai Tongji Clearon Environmental-Protection Equipment Engineering Co., Ltd, Shanghai 200092, P. R. China

E-mail: fanjianwei@tongji.edu.cn; jianpingyang@dhu.edu.cn

Tel: +86-21-65985885

Table S1. Element contents of PdCu@OMC obtained from EDX results.

Element	C	Pd	Cu
Weight percentage (%)	77.58	17.42	4.99
Atom percentage (%)	96.38	2.44	1.17