

Ion Exchange Induced Removal of Pb(II) by MOF-Derived Magnetic Inorganic Sorbents

Dezhi Chen^a, Weisong Shen^a, Shaolin Wu^{*a}, Caiqing Chen^a, Xubiao Luo^{*a}, Lin Guo^{*a,b}

^a Key Laboratory of Jiangxi Province for Persistent Pollutants Control and Resources Recycle, School of Environmental and Chemical Engineering, Nanchang Hangkong University, Nanchang 330063, P. R. China

^b Key Laboratory of Bio-Inspired Smart Interfacial Science and Technology of Ministry of Education, School of Chemistry and Environment, Beihang University, Beijing 100191, P. R. China

*Corresponding authors: Tel & Fax: 86(0)791 839 533 73

Email address: luoxubiao@nchu.edu.cn (X. Luo); 39008@nchu.edu.cn (S. Wu);

guolin@buaa.edu.cn (L. Guo)

Supporting information

Table S1. Comparison of maximum adsorption Capacities (mg g⁻¹) with various adsorbents for removal of Pb(II)

Adsorbent sample	Adsorption capacity (mg g ⁻¹)	Reference
Fe ₃ O ₄	36.01	1
amino-functionalized Fe ₃ O ₄ @SiO ₂	111.9	2
ZnO@SiO ₂ @Fe ₃ O ₄ /C	54.6	3
ZnO nanosheets	6.7	4
ZnO nanoparticles	50.0	5
Modified-ZnO nanopowders	61.2	6
Grapheme-ZnO	23.42	7
nano-TiO ₂	30.8	8
Nano Iron oxides	71.464	9
Nano-CuO	188.67	10
Polyethersulfone/hydrous manganese dioxide	204.1	11
Modified inorganic mesoporous silica	200.80	12
Amino siloxane oligomer-linked graphene oxide	312.5	13
PVA/PAA gel	194.99	14

triethylmethyl ammonium carboxymethylated chitosan ZnO/ZnFe ₂ O ₄ /C	143.3	15
	344.83	this work




Figure S1. XRD pattern of Pb(NO₃)₂

Table S2. The intensity ratios of main diffraction peaks for ZnO and ZnFe₂O₄ before and after Pb(II) adsorption according to the XRD patterns of ZnO/ZnFe₂O₄/C and ZnO/ZnFe₂O₄/C-Pb.

	ZnO				ZnFe ₂ O ₄ /ZnO
	I ₍₁₀₀₎ /I ₍₁₀₁₎	I ₍₀₀₂₎ /I ₍₁₀₁₎	I ₍₁₀₂₎ /I ₍₁₀₁₎	I ₍₁₁₂₎ /I ₍₁₀₁₎	I _(311-ZnFe2O4) /I _(101-ZnO)
ZnO/ZnFe ₂ O ₄ /C	0.728	0.405	0.172	0.191	0.393
ZnO/ZnFe ₂ O ₄ /C-Pb	0.758	0.390	0.174	0.190	0.472
	ZnFe ₂ O ₄				
	I ₍₂₂₀₎ /I ₍₃₁₁₎	I ₍₀₁₂₎ /I ₍₃₁₁₎			
ZnO/ZnFe ₂ O ₄ /C	0.291	0.222			
ZnO/ZnFe ₂ O ₄ /C-Pb	0.297	0.227			




Figure S2. XPS spectra of ZnO/ZnFe₂O₄/C and ZnO/ZnFe₂O₄/C-Pb. (a) Pb 4d, (b) Fe 2p, (c) Zn 2p, (d) C 1s.




Figure S3. EDS and mapping images of ZnO/ZnFe₂O₄/C-Pb.




Figure S4. N₂ adsorption-desorption isotherm and the pore-size distribution curve of
ZnO/ZnFe₂O₄/C

Reference

1. N. N. Nassar, *Journal of hazardous materials*, 2010, **184**, 538-546.
2. J. Wang, S. Zheng, Y. Shao, J. Liu, Z. Xu and D. Zhu, *Journal of colloid and interface science*, 2010, **349**, 293-299.
3. X. M. Zhang, J. Y. Liu, S. J. Kelly, X. J. Huang and J. H. Liu, *Journal of Materials Chemistry A*, 2014, **2**, 11759-11767.
4. X. Ma, Y. Wang, M. Gao, H. Xu and G. Li, *Catalysis Today*, 2010, **158**, 459-463.
5. S. Mahdavi, M. Jalali and A. Afkhami, *Journal of Nanoparticle Research*, 2012, **14**.
6. S. Nekouei, F. Nekouei, I. Tyagi, S. Agarwal and V. K. Gupta, *Process Safety and Environmental Protection*, 2016, **99**, 175-185.
7. X. Zhao, B. Hu, J. Ye and Q. Jia, *Journal of Chemical & Engineering Data*, 2013, **58**, 2395-2401.
8. Z. Jin, H. Gao and L. Hu, *Rsc Advances*, 2015, **5**, 88520-88528.
9. C. Zhang, Z. Yu, G. Zeng, B. Huang, H. Dong, J. Huang, Z. Yang, J. Wei, L. Hu and Q. Zhang, *Chemical Engineering Journal*, 2016, **284**, 247-259.
10. L. Arfaoui, S. Kouass, H. Dhaouadi, R. Jebali and F. Touati, *Materials Research Bulletin*, 2015, **70**, 284-290.
11. R. Jamshidi Gohari, W. J. Lau, T. Matsuura, E. Halakoo and A. F. Ismail, *Separation and Purification Technology*, 2013, **120**, 59-68.
12. M. R. Awual, M. M. Hasan and A. Shahat, *Sensors and Actuators B: Chemical*, 2014, **203**, 854-863.
13. S. Luo, X. Xu, G. Zhou, C. Liu, Y. Tang and Y. Liu, *Journal of Hazardous Materials*, 2014, **274**, 145-155.
14. L. Chu, C. Liu, G. Zhou, R. Xu, Y. Tang, Z. Zeng and S. Luo, *Journal of Hazardous Materials*, 2015, **300**, 153-160.
15. H. Cui, J. Chen, H. Yang, W. Wang, Y. Liu, D. Zou, W. Liu and G. Men, *Chemical Engineering Journal*, 2013, **232**, 372-379.