

Table S1 The Impact and flexural strengths of DCPDCE resin and HPP-GO/DCPDCE composites

samples	Impact strength (KJ/m ²)	flexural strength (MPa)
DCPDCE	9.5	94.0
0.2 wt% HPP-GO/DCPDCE	10.7	104.0
0.4 wt% HPP-GO/DCPDCE	13.3	117.0
0.6 wt% HPP-GO/DCPDCE	16.8	146.3
0.8 wt% HPP-GO/DCPDCE	17.5	136.9




Fig S1