

Electronic Supplementary Information

Synthesis of aminopropyltriethoxysilane grafted/tripolyphosphate intercalated ZnAl LDHs and its performance in the flame retardancy and smoke suppression of polyurethane elastomer

**Wenzong Xu,<sup>\*ab</sup> Shaoqing Wang,<sup>a</sup> Aijiao Li<sup>a</sup> and Xiaoling Wang<sup>a</sup>**

<sup>a</sup>School of Materials Science and Chemical Engineering, Anhui Jianzhu University, 292 Ziyun Road, Hefei 230601, Anhui Province, P.R. China

<sup>b</sup>State Key Lab of Fire Science, University of Science and Technology of China, Hefei 230026, Anhui Province, P.R. China

Correspondence to: Wenzong Xu (\*Tel./Fax:+86-0551-63828157. E-mail:wenzongxu@ahjzu.edu.cn)




Fig. S1 TG curves of LDHs




Fig. S2 THR curves of PUE/LDHs composites

Table S1 Characteristic data from TG analysis of PUE/LDHs composites

Samples	Temperature(°C)				Char (%)
	T <sub>5</sub> <sup>a</sup>	T <sub>10</sub> <sup>a</sup>	T <sub>50</sub> <sup>a</sup>	T <sub>max</sub> <sup>b</sup>	
PUE0	305	324	435	457	<0.1
PUE1	295	316	415	420	0.5
PUE3	285	302	396	404	2.8
PUE5	277	295	382	383	6.6
PUE6	299	321	418	425	0.5
PUE8	297	319	402	407	2.8
PUE10	295	316	393	395	8.2

<sup>a</sup> T<sub>5</sub>, T<sub>10</sub>, T<sub>50</sub>, temperature at which 5%,10%,50% weight loss occurs

<sup>b</sup> T<sub>max</sub>, temperature at which maximum weight loss occurs

Table S2 Smoke density of PUE/LDHs composites

Samples	D <sub>s,max</sub>	D <sub>s,10min</sub>	Samples	D <sub>s,max</sub>	D <sub>s,10min</sub>
PUE0	421	391	—	—	—
PUE1	362	347	PUE 6	306	286
PUE2	345	311	PUE 7	224	190
PUE3	315	274	PUE 8	204	178
PUE4	220	196	PUE 9	182	176
PUE5	208	192	PUE 10	180	162