

Supporting Information

The use of solvent-soaking treatment to enhance the anisotropic mechanical properties of electrospun nanofiber membranes for water filtration

Jie Cai,^{a,b*} Qian Zhang,^a Miao Lei,^a Jingren He,^a Gang Liu,^{a*}

^a *College of Food Science and Engineering, Wuhan Polytechnic University, Wuhan 430023, PR China*

^b *College of Food Science and Technology, Huazhong Agricultural University, Wuhan 430070, PR China*

*Corresponding authors at: College of Food Science and Engineering, Wuhan Polytechnic University, Wuhan 430023, PR China

E-mail: caijievip@hotmail.com; caijievip@whpu.edu.cn (Dr. Jie Cai); lg820823@163.com (Dr. Gang Liu)

Table S1 Assignments of main infrared absorption bands in cellulosic materials

Wave number (cm ⁻¹)		Assignment
BC	B-CA	
3332	3490	OH stretching
	2952	CH stretching of CH ₂
2901	2901	
1734		C=O stretching of acetyl or carboxylic acid
	1745	C-O stretching of ester
		H-O-H bending of absorbed water and/or C=O stretching
1641		amid
	1639	H-O-H bending of absorbed water
1423	1435	CH ₂ bending or OH in plane bending
1368	1372	C-H deformation (CH ₃ or OH in plane bending)
	1236	C-O stretching of acetyl group
1162	1165	C-O-C antisymmetric bridge stretching
1024	1037	C-O-C symmetric stretching of primary alcohol
883	902	β glucosidic linkages between the sugar units




Figure S1 ATR-FTIR spectrum of B-CA NFMs (treated and untreated)