

	Static Contact Angle (°)		
	Untreated	Soaked in Water	Soaked in Culture Medium
Superhydrophobic Surfaces	162.3±2.3	159.2±3.0	156.1±3.8
OCP-1	6.1±0.7	7.5±1.1	9.1±0.9
OCP-2	8.3±0.5	8.1±0.9	10.4±2.3
OCP-3	9.4±0.9	8.7±1.5	9.7±1.8
OCP-4	11.9±1.4	12.5±2.2	14.5±0.8

Table S2. The results of the static water contact angle of the superhydrophobic surfaces and each of the OCP surfaces after soaking in water for 3 days, soaking in cell culture medium for 3 days and untreated.