Supporting Information

Silver Nanowire Networks Embedded in Cure-Controlled Optical Adhesive Film for a Transparent and Highly Conductive Electrode

Hong Suk Kang,^{1,3} *Jaeho Choi*,¹ *Wonhee Cho*,¹ *Hongkyung Lee*,¹ *Dongyoung Lee*,² *Dai Gil Lee*,² and *Hee-Tak Kim*¹*

¹Department of Chemical and Biomolecular Engineering, Korea Advanced Institute of Science and Technology (KAIST), Daejeon, 305-701, South Korea ²School of Mechanical Aerospace & Systems Engineering, Korea Advanced Institute of Science and Technology (KAIST), Daejeon, 305-701, South Korea ³Department of Materials Science and Engineering, University of Pennsylvania, 3231 Walnut Street, Philadelphia, PA 19104, USA

*Email - heetak.kim@kaist.ac.kr



Figure S1. (a) Low and (b) magnification SEM images of AgNW network



Figure S2. Stress-strain curve of NOA 85: Strain range (a) from 0 to 0.2, (b) from 0 to 0.15, and (c) from 0.1483 to 0.1485.



Figure S3. SEM image of as-deposited AgNW film after lightly rubbing the surface. Most AgNWs are removed due to low adhesion between AgNWs and substrate.



Figure S4. SEM images of (a) as-deposited AgNW film and (b) AgNW/NOA 85 composite film after exposure in the atmosphere at room temperature for 2 weeks. The as-deposited AgNW film shows more severe oxygen corrosion than that of the AgNW/NOA 85 composite film.