

A summary of bond lengths and angles should also be presented.

Table Selected Bond Lengths

Atom	Atom	Length/Å
Co02	O31	1.880 (2)
Co02	O18	2.019 (3)
Co02	O18 ¹	2.019 (3)
Co02	O2 ¹	2.009 (3)
Co02	O2	2.009 (3)
Co02	O23	2.121 (5)
Co01	O31	1.892 (5)
Co01	O12	2.100 (6)
Co01	O1	2.009 (3)
Co01	O1 ¹	2.009 (3)
Co01	O1 ²	2.009 (3)
Co01	O1 ³	2.009 (3)
Fe02	O31	1.880 (2)
Fe02	O18 ¹	2.019 (3)
Fe02	O18	2.019 (3)
Fe02	O2	2.009 (3)
Fe02	O2 ¹	2.009 (3)
Fe02	O23	2.121 (5)
Fe01	O31	1.892 (5)
Fe01	O12	2.100 (6)
Fe01	O1 ¹	2.009 (3)
Fe01	O1 ²	2.009 (3)
Fe01	O1 ³	2.009 (3)
Fe01	O1	2.009 (3)
Cr02	O31	1.880 (2)
Cr02	O18 ¹	2.019 (3)
Cr02	O18	2.019 (3)
Cr02	O2 ¹	2.009 (3)
Cr02	O2	2.009 (3)
Cr02	O23	2.121 (5)
Cr01	O31	1.892 (5)
Cr01	O12	2.100 (6)
Cr01	O1 ¹	2.009 (3)
Cr01	O1 ²	2.009 (3)
Cr01	O1 ³	2.009 (3)

Table Selected Bond Angles

Atom	Atom	Atom	Angle/°	Atom	Atom	Atom	Angle/°
O31	Co02	O18 ¹	96.32 (13)	O2	Fe02	O23	84.47 (13)
O31	Co02	O18	96.32 (13)	O2 ¹	Fe02	O23	84.47 (13)
O31	Co02	O2 ¹	95.06 (12)	O31	Fe01	O12	180.0
O31	Co02	O2	95.06 (12)	O31	Fe01	O1 ³	95.12 (9)
O31	Co02	O23	179.33 (18)	O31	Fe01	O1	95.12 (9)
O18 ¹	Co02	O18	90.0 (2)	O31	Fe01	O1 ¹	95.12 (9)
O18	Co02	O23	84.16 (13)	O31	Fe01	O1 ²	95.12 (9)
O18 ¹	Co02	O23	84.16 (13)	O1 ³	Fe01	O12	84.88 (9)
O2	Co02	O18 ¹	87.91 (15)	O1	Fe01	O12	84.88 (9)
O2 ¹	Co02	O18 ¹	168.59 (14)	O1 ²	Fe01	O12	84.88 (9)
O2	Co02	O18	168.59 (13)	O1 ¹	Fe01	O12	84.88 (9)
O2 ¹	Co02	O18	87.91 (15)	O1 ²	Fe01	O1	169.75 (18)
O2 ¹	Co02	O2	91.9 (2)	O1 ³	Fe01	O1	86.6 (2)
O2	Co02	O23	84.47 (13)	O1 ³	Fe01	O1 ¹	169.75 (18)
O2 ¹	Co02	O23	84.47 (13)	O1 ³	Fe01	O1 ²	92.5 (2)
O31	Co01	O12	180.0	O1 ¹	Fe01	O1 ²	86.6 (2)
O31	Co01	O1 ²	95.12 (9)	O1 ¹	Fe01	O1	92.5 (2)
O31	Co01	O1 ³	95.12 (9)	O31	Cr02	O18 ¹	96.32 (13)
O31	Co01	O1 ¹	95.12 (9)	O31	Cr02	O18	96.32 (13)
O31	Co01	O1	95.12 (9)	O31	Cr02	O2	95.06 (12)
O1 ¹	Co01	O12	84.88 (9)	O31	Cr02	O2 ¹	95.06 (12)
O1	Co01	O12	84.88 (9)	O31	Cr02	O23	179.33 (18)
O1 ²	Co01	O12	84.88 (9)	O18 ¹	Cr02	O18	90.0 (2)
O1 ³	Co01	O12	84.88 (9)	O18 ¹	Cr02	O23	84.16 (13)
O1 ²	Co01	O1	169.75 (18)	O18	Cr02	O23	84.16 (13)
O1 ³	Co01	O1	86.6 (2)	O2	Cr02	O18 ¹	87.91 (15)
O1 ¹	Co01	O1	92.5 (2)	O2	Cr02	O18	168.59 (13)
O1 ³	Co01	O1 ²	92.5 (2)	O2 ¹	Cr02	O18	87.91 (15)
O1 ¹	Co01	O1 ²	86.6 (2)	O2 ¹	Cr02	O18 ¹	168.59 (14)
O1 ³	Co01	O1 ¹	169.75 (18)	O2 ¹	Cr02	O2	91.9 (2)
O31	Fe02	O18	96.32 (13)	O2 ¹	Cr02	O23	84.47 (13)
O31	Fe02	O18 ¹	96.32 (13)	O2	Cr02	O23	84.47 (13)
O31	Fe02	O2 ¹	95.06 (12)	O31	Cr01	O12	180.0
O31	Fe02	O2	95.06 (12)	O31	Cr01	O1	95.12 (9)
O31	Fe02	O23	179.33 (18)	O31	Cr01	O1 ¹	95.12 (9)
O18 ¹	Fe02	O18	90.0 (2)	O31	Cr01	O1 ²	95.12 (9)
O18 ¹	Fe02	O23	84.16 (13)				
O18	Fe02	O23	84.16 (13)				
O2	Fe02	O18 ¹	87.91 (15)				
O2 ¹	Fe02	O18	87.91 (15)				
O2 ¹	Fe02	O18 ¹	168.59 (14)				
O2	Fe02	O18	168.59 (13)				
O2 ¹	Fe02	O2	91.9 (2)				

