

Electrochemical behavior of glycine-mediated N-doped reduced graphene oxide

Mahima Khandelwal and Anil Kumar*

Department of chemistry, Indian Institute of Technology Roorkee, Roorkee-247667, India.
E-mail: anilkfcy@iitr.ac.in; akmshfcy@gmail.com




Fig. S1: Raman spectrum of GO.




Fig. S2: EDAX spectrum of N-rGOGly.

Table S1: Raman spectral data of Graphene Oxide, N-rGOGly and N-rGOGly300

Sample(s)	D band (cm⁻¹)	G band (cm⁻¹)	I_D/I_G
GO	1351	1603	0.90
N-rGOGly	1350	1605 (D' 1620)	1.01
N-rGOGly300	1357	1595 (D' 1609)	0.98