

Electronic Supplementary Material (ESI) for RSC Advances.

This journal is © The Royal Society of Chemistry 2016

Supplementary data

Selective hydrodeoxygenation of 5-hydroxymethylfurfural to 2, 5-dimethylfuran on Ru-MoOx/C catalysts

Yue Yang^a, Qiyang Liu^{*,b}, Dan Li^b, Jin Tan^b, Qi Zhang^b, Chenguang Wang^b, Longlong Ma^{*,b}

^aDepartment of Chemistry, University of Science and Technology of China, Hefei 230026, P. R. China

^bKey Laboratory of Renewable Energy, Guangzhou Institute of Energy Conversion, Chinese Academy of Sciences, Guangzhou 510640, P. R. China.

Corresponding author: mall@ms.giec.ac.cn

(Longlong Ma),

liuqy@ms.giec.ac.cn (Qiyang Liu)




Fig. S1 NH₃-temperature-programmed desorption profiles of 5%Ru-20%MoOx/C, 5%Ru-10%MoOx/C, 5%Ru-5%MoOx/C and 5%Ru/C catalysts.

Table S1: the Acidity of of catalysts^a

Catalysts	Acidity(mmol/g)
5%Ru-20%MoO _x /C	0.73
5%Ru-10%MoO _x /C	0.68
5%Ru-5%MoO _x /C	0.57
5%Ru /C	0.33

^a NH₃-TPD technique (total acidic amount)




Fig. S2 Effect of the concentration of products with time. Reaction condition: 120 °C, HMF 0.5 g, n-butyl alcohol 40 ml, 5%Ru-10%MoO_x/C catalyst 0.1 g.