Supplementary Information for

## Influence from the types of surface functional groups of RGO on

## the performances of thermal interface materials

Yunfei Sun<sup>a\*</sup>, Yanfeng He<sup>b</sup>, Bo Tang<sup>b\*</sup>, Chongben Tao<sup>a</sup>, Jianmin Ban<sup>a</sup>, Li Jiang<sup>a</sup>

<sup>a</sup>College of Electronic and Information Engineering, Suzhou University of Sciences and Technology, Suzhou, Jiangsu 215009, People's Republic of China

<sup>b</sup>School of Petroleum Engineering, Changzhou University, Changzhou city 213016, China. Corresponding authors: 113965203@qq.com; tangbo@cczu.edu.cn.




Fig. S1 Stress-strain curves of the pristine ER and resulting TIMs.

 Table S1 Mechanical performances of various samples.

Properties Samples	Ultimate strength (enhancement factor)	Stretch limits (strain %)			
			Pristine ER	1	230
			RGO (h, e)-5 wt%	0.98	220
RGO (x, e)-5 wt%	0.97	220			
RGO (h, h)-5 wt%	0.94	200			
RGO (x, h)-5 wt%	0.94	210			
RGO (h, e)-10 wt%	0.96	210			
RGO (x, e)-10 wt%	0.96	210			
RGO (h, h)-10 wt%	0.93	210			
RGO (x, h)-10 wt%	0.92	200			