Electronic Supplementary Material (ESI) for Journal of Materials Chemistry C. This journal is © The Royal Society of Chemistry 2017

1 Supplementary Information

# 2 Copper-Embedded Reduced Graphene Oxide Fiber

3

## for Multi-sensor

4 Chang Su Yeo<sup>‡ab</sup>, Hyunjin Kim<sup>‡c</sup>, Taekyung Lim<sup>d</sup>, Hyuk Joon Kim<sup>ac</sup>, Sanghun Cho<sup>c</sup>, Kang Rae Cho<sup>e</sup>, Youn

5 Sang Kim<sup>ac</sup>, Min Kyoon Shin<sup>a</sup>, Jeeyoung Yoo<sup>\*c</sup>, Sanghyun Ju<sup>\*d</sup>, and Sang Yoon Park<sup>\*a</sup>

6

<sup>7</sup> <sup>a</sup>Advanced Institutes of Convergence Technology, Seoul National University, Suwon-si, Gyeonggi-do
8 16229, Republic of Korea

9 <sup>b</sup>Department of Physics, Sungkyunkwan University, Suwon, South Korea

10 °Program in Nano Science and Technology, Graduate School of Convergence Science and Technology,

11 Seoul National University, Seoul 08826, Republic of Korea

12 <sup>d</sup>Department of Physics, Kyonggi University, Suwon 443-270, Republic of Korea

13 eDepartment of Research and Development, Puritech Inc., Pyeongtaek 459-040, Republic of Korea

14 *†*These authors contributed equally to this work.

15

#### 17 1. Size information of GO





### 21 2. Fabricated CROG fibers

CRGO-1	CRG0-1	CRGO-4
CRGO-2		
0000		
CRGO-4	1 wt% CuCl <sub>2</sub> -EG	10 wt% CuCl <sub>2</sub> -EG

- Figure S2. Photo image of a CRGO fiber longer than 30 cm fabricated in a co-flow wet-spinning
- 24 machine with different concentrations of  $CuCl_2$  in EG (CRGO-1, CRGO-2, CRGO-3, and CRGO-4).

25





29 Figure S3. Line profiles of FFT frequency domain images of CRGO fibers





Figure S4. Size distribution of CuI and Cu particles calculated from the SEM images (A), and standard
 deviation of the particle size (B)

35 5. Sensitivity of CRGO fibers to chlorobenzene and temperature.



Figure S5. (A) Gas sensitivity of CRGO fibers for three different evaporation rates (2.78 μg/s, 4.72 μg/s, and 5.14 μg/s). (B) Temperature sensitivity of CRGO fibers for four different temperature (25 °C, 30 °C, 39 35 °C, and 40 °C).