

Controlling Magnetism via Transition Metal Exchange in the Series of Intermetallics $\text{Eu}(T1,T2)_5\text{In}$ ($T = \text{Cu}, \text{Ag}, \text{Au}$)

Volodymyr Smetana,^a Yaroslav Mudryk,^b Vitalij K. Pecharsky,^{b,c} Anja-Verena Mudring*,^a

^a Department of Materials and Environmental Chemistry, Stockholm University, Svante Arrhenius väg 16 C, 106 91 Stockholm, Sweden

^b Ames Laboratory, U.S. Department of Energy, Iowa State University, Ames, Iowa 50011-3020, USA

^c Department of Materials Science and Engineering, Iowa State University, Ames, Iowa 50011-2300, USA

Electronic Supplementary Information

Table S1. Critical Field (H_{cr}) at 2 K of the metamagnetic-like transformations in $\text{EuAu}_x\text{Cu}_{5-x}\text{In}$ alloys as a function of $x(\text{Au})$

$x(\text{Au})$	H_{cr} , kOe
2.66	36
3.03	30
3.94	16
4.61	0