

PCCP



Supporting Information

Tuning the size of gold nanoparticles produced by multiple filamentation of femtosecond laser pulses in aqueous solution.

Hakim Belmouaddine,^{*a} Minghan Shi,^a Léon Sanche^a and Daniel Houde^{*a}

^a Department of Nuclear Medicine and Radiobiology, Faculty of Medicine and Health Sciences, University of Sherbrooke, Sherbrooke, QC, J1H 5N4 (Canada).
Fax: +1 819 564 5442; Tel: +1 819 346 1110 ext. 74345.

* Authors to whom correspondence should be addressed. E-mail: hakim.belmouaddine@usherbrooke.ca

Representative Transmission Electron Microscopy images of gold nanoparticles




Fig. S1 Representative TEM images of laser-induced gold nanoparticles after 26 min of irradiation at $I \sim 2.4 \times 10^{11} \text{ W.cm}^{-2}$ of 0.1 M PVA, 1 mM gold chloride (HAuCl_4) solutions




Fig. S2 Representative TEM images of radiation-induced gold nanoparticles after 180 min of irradiation at $I \sim 10 \text{ Gy} \cdot \text{min}^{-1}$ of 0.1 M PVA, 1 mM gold chloride (HAuCl_4) solutions




Fig. S3 Representative TEM images of laser-induced gold nanoparticles after 59 min of irradiation at $I \sim 1.9 \times 10^{11} \text{ W.cm}^{-2}$ of 0.1 M PVA, 1 mM gold chloride (HAuCl_4) solutions




Fig. S4 Representative TEM images of laser-induced gold nanoparticles after 142 min of irradiation at $I \sim 1.6 \times 10^{11} \text{ W.cm}^{-2}$ of 0.1 M PVA, 1 mM gold chloride (HAuCl_4) solutions