


Supplementary Material S1



Elt.	Line	Intensity (c/s)	Error 2-sig	Atomic %	Conc	Units	
C	Ka	8.60	0.415	56.270	48.369	wt.%	
N	Ka	0.00	0.000	0.000	0.000	wt.%	
O	Ka	3.50	0.265	36.463	41.752	wt.%	
F	Ka	0.69	0.118	8.667	9.880	wt.%	
				100.000	100.000	wt.%	Total

kV 2.0
Takeoff Angle 35.0°
Elapsed Livetime 200.0

EDX of fluoropolymer modified cotton fabric

