New Journal of Chemistry

Electronic Supporting Information

## Uranyl oxide hydrate phases with heavy lanthanide ions: $[Ln(UO_2)_2O_3(OH)] \cdot 0.5H_2O$ (Ln = Tb, Dy, Ho and Yb)

Yingjie Zhang,\*<sup>a</sup> Robert Aughterson,<sup>a</sup> Inna Karatchevtseva,<sup>a</sup> Linggen Kong,<sup>a</sup> Toan Trong Tran,<sup>b</sup> Jiří Čejka,<sup>c</sup> Igor Aharonovich,<sup>b</sup> Gregory R. Lumpkin<sup>a</sup>

<sup>a</sup> Nuclear Fuel Cycle Research Theme, Australian Nuclear Science and Technology Organisation, Locked Bag 2001, Kirrawee DC, NSW 2232, Australia.

<sup>b</sup> School of Physics and Advanced Materials, University of Technology Sydney, Ultimo, New South Wales 2007, Australia.

<sup>c</sup> Department of Mineralogy and Petrology, National Museum Cirkusová 1740, 193 00 Prague 9, Czech Republic.

\* Corresponding author: Email: <u>yzx@ansto.gov.au</u>



Fig. S1. Observed (crosses), calculated and difference (solid lines) diffraction profiles for samples 2 (top) and 3 (bottom).



Fig. S2. SEM-EDS spectra for samples 1 (a), 2 (b) and 3 (c).



Fig. S3. SEM-EDS element mapping for sample 1.



Fig. S4. SEM-EDS element mapping for sample 2.



Fig. S5. SEM-EDS element mapping for sample 3.



Fig. S6. SEM-EDS element mapping for sample 4.



Fig. S7. Infrared spectra of samples 1 (top) and 2 (bottom).

Н	K	L	d-spacing			
			1	2	3	4
0	0	1	8.279552	8.257188	8.269512	8.202184
0	0	2	4.139795	4.128571	4.134841	4.101059
0	1	0	3.408896	3.405309	3.398158	3.395611
0	1	1	3.152243	3.148101	3.143101	3.13736
0	0	3	2.75978	2.752343	2.756552	2.734015
0	1	2	2.631501	2.627007	2.625289	2.615474
0	1	3	2.145001	2.140584	2.140729	2.129553
0	0	4	2.069857	2.064287	2.067383	2.050546
1	1	0	1.968161	1.966063	1.961923	1.96048
1	1	1	1.914783	1.91258	1.908946	1.906758
1	1	2	1.777497	1.775081	1.772512	1.76877
0	1	4	1.769249	1.765268	1.76619	1.755325
0	2	0	1.70446	1.702671	1.699077	1.697824
0	2	1	1.669469	1.667567	1.664305	1.662582
0	0	5	1.655869	1.651427	1.653919	1.640442
1	1	3	1.602418	1.599821	1.598399	1.593219
0	2	2	1.576114	1.574054	1.571562	1.568714
0	1	5	1.489455	1.485916	1.487115	1.477101
0	2	3	1.450192	1.447995	1.446388	1.44235
1	1	4	1.426287	1.423674	1.423114	1.417029
0	0	6	1.379905	1.376194	1.37826	1.367023
0	2	4	1.315767	1.313498	1.312644	1.307735
1	2	0	1.288467	1.287082	1.284383	1.283426
0	1	6	1.279086	1.27593	1.277196	1.268125
1	2	1	1.273144	1.271727	1.269168	1.268009
1	1	5	1.267084	1.26452	1.264534	1.258097
1	2	2	1.230255	1.22876	1.226566	1.224858

 Table S1. Calculated d-spacing from XRD patterns for UOH phases 1-4.