

***Scalable synthesis of environmentally benign graphene-sand
based organic-inorganic hybrid for sulfide removal from
aqueous solution: an insight into the mechanism***

Anjali Achazhiyath Edathil, Jerina Hisham Zain*, Mohammad Abu Haija , Fawzi Banat*

Department of Chemical Engineering, Khalifa University - SAN campus

Abu Dhabi, United Arab Emirates

*Email of corresponding author: jerina.zain@ku.ac.ae ; fawzi.banat@ku.ac.ae

Table S1. Statistical analysis of the effect of pH on sulfide adsorption.

| pH | 2.82 | 4.12 | 5.64 | 6.04 | 7.58 | 9.18 | 10.21 | 11.06 | 12.06 |
|---------------------------|-------------|-------------|-------------|-------------|-------------|-------------|--------------|--------------|--------------|
| % Removal | 100 | 100 | 99.8 | 99.8 | 99.6 | 99.8 | 100 | 99.6 | 100 |
| | 100 | 99.9 | 100 | 99.7 | 99.9 | 100 | 99.7 | 99.7 | 100 |
| | 99.8 | 99.8 | 99.9 | 100 | 100 | 99.8 | 99.9 | 100 | 99.9 |
| Mean | 99.93 | 99.90 | 99.90 | 99.83 | 99.83 | 99.87 | 99.87 | 99.77 | 99.97 |
| Variance | 0.01 | 0.01 | 0.01 | 0.02 | 0.04 | 0.01 | 0.02 | 0.04 | 0.00 |
| Standard Deviation | 0.12 | 0.10 | 0.10 | 0.15 | 0.21 | 0.12 | 0.15 | 0.21 | 0.06 |
| Standard Error | 0.07 | 0.06 | 0.06 | 0.09 | 0.12 | 0.07 | 0.09 | 0.12 | 0.03 |