

Supporting Information

Low-cost, Flexible and Regular-array Three-dimensional Nanopyramid Antibacterial Films for Clinical Applications

Kwong-Hoi Tsui^{1†}, Xin Li^{2, 4†}, James K.H. Tsoi³, Siu-Fung Leung¹, Lei Tang¹, Wing Yi Chak¹, Chengfei Zhang², Jiang Chen⁴, Gary S.P. Cheung^{2*}, Zhiyong Fan^{1*}

¹ Department of Electronic and Computer Engineering, The Hong Kong University of Science and Technology, Clear Water Bay, Kowloon, Hong Kong SAR, China

² Discipline of Endodontology, Faculty of Dentistry, The University of Hong Kong, Sai Ying Pun, Hong Kong SAR, China

³ Dental Materials Science, Faculty of Dentistry, The University of Hong Kong, Sai Ying Pun, Hong Kong SAR, China

⁴ Department of Oral Implantology, Affiliated Stomatological of Fujian Medical University, Fuzhou, Fujian 350002, China

* Corresponding author: eezfan@ust.hk, spcheung@hku.hk

† These authors (K-H Tsui and X. Li) contribute equally

List of Contents

1. Summary of CLSM result. a) Summary of Live *E.coli* and b) Summary of Dead *E.coli*

Supplementary Information

a

Number of Live *E.coli*

x10 ³	<u>Planar</u>	<u>NPA</u>	<u>NPB</u>	<u>NPC</u>
1-hr	17.3 (±0.18)	2.0 (±0.02)	1.5 (±0.02)	1.5 (±0.02)
24-hr	59.4 (±1.18)	2.3 (±0.02)	2.0 (±0.03)	1.4 (±0.02)
72-hr	26.6 (±0.34)	0.4 (±0.01)	0.6 (±0.03)	1.2 (±0.03)
168-hr	61.5 (±0.58)	3.6 (±0.05)	3.3 (±0.07)	5.7 (±0.04)

b

Number of Dead *E.coli*

x10 ³	<u>Planar</u>	<u>NPA</u>	<u>NPB</u>	<u>NPC</u>
1-hr	0.2 (±0.00)	0.2 (±0.01)	0.1 (±0.00)	0.1 (±0.00)
24-hr	0.0 (±0.00)	0.3 (±0.01)	0.3 (±0.01)	0.2 (±0.00)
72-hr	0.8 (±0.03)	0.6 (±0.02)	0.7 (±0.03)	1.2 (±0.03)
168-hr	0.1 (±0.00)	2.8 (±0.07)	2.8 (±0.03)	5.8 (±0.02)

Supporting information Table S1 Summary of CLSM result. a) Summary of Live *E.coli* and b) Summary of Dead *E.coli*