

Supplementary Information

Electrospinning of Highly Aligned Fibers for Drug Delivery Applications

*Mohammad Javad Eslamian, Milad Khorrami, Ning Yi, Sheereen Majd, Mohammad Reza Abidian**




Figure S1. Histogram size distribution of PLGA fibers with electrospinning setup of $V = 12\text{kV}$, $Q = 400\text{ }\mu\text{l.hr}^{-1}$, $w = 1000\text{ rpm}$, $d = 0.41\text{ mm}$, and $l = 14\text{ cm}$. (diameter $2.82 \pm 0.7\text{ }\mu\text{m}$, $n=100$)