Electronic Supplementary Material (ESI) for Journal of Materials Chemistry C. This journal is © The Royal Society of Chemistry 2018

Supplementary Information

The Contribution of Hydrogen Bonding to the Photomechanical Response of Azobenzene-functionalized Polyamides

Jeong Jae Wie, ^{§,a,b,c} David H. Wang, ^{§,a,d}, Kyung Min Lee, ^{a,b} Timothy J. White^{a,*} and Loon-Seng Tan^{a,*}

^a Materials & Manufacturing Directorate, Air Force Research Laboratory, Wright-Patterson Air Force Base, Ohio 45433-7750, USA ^bAzimuth Corp. Dayton, OH 45432, USA

^cDepartment of Polymer Science and Engineering, Inha University, Incheon 22212, South

Korea

^dUES Inc., Dayton Ohio, 45432, USA

§ These authors contributed equally

*Email: loon.tan@us.af.mil or timothy.white.24@us.af.mil

List of Figures

Fig. S1. Polarized optical micrographs of (a) azoPA and (b) azoPI films on crossed polarizers at different sample angles.

Fig. S2. Comparison of FT-IR spectra of PA and azoPA films. Since both spectra contain essentially the same band at 1402-1403 cm⁻¹ that falls in the range of 1400-1450 cm⁻¹ for the IR-active azo (N=N) stretching vibration for unsymmetrical azobenzene compounds,[1] this band cannot be assigned as the azo band for azoPA.

Fig. S3. DMA results of azoPA film before any irradiation (black line), and after irradiation with polarized (E/X) 445nm blue light for 60 min, immediately followed by storage in darkness for 2 days; (a) Plots of storage modulus, (b) loss modulus, and tan delta vs. temperature.



Fig. S1. Polarized optical micrographs of (a) azoPA and (b) azoPI films on crossed polarizers at different sample angles.



Fig. S2. Comparison of FT-IR spectra of PA and azoPA films. Since both spectra contain essentially the same band at 1402-1403 cm⁻¹ that falls in the range of 1400-1450 cm⁻¹ for the IR-active azo (N=N) stretching vibration for unsymmetrical azobenzene compounds,[1] this band cannot be assigned as the azo band for azoPA.



Fig. S3. DMA results of azoPA film before any irradiation (black line), and after irradiation with polarized (E//X) 445nm blue light for 60 min, immediately followed by storage in darkness for 2 day. (a) Plots of storage modulus, (b) loss modulus, and tan delta vs. temperature.

Reference

[1] N. B. Colthup, L. H. Daly and S. E. Wiberley, Introduction to Infrared and Raman Spectroscopy, 3rd Ed, Academic Press, 1990, San Diego, CA USA, pg.351.