

Figure S1

a.

Sample	Molar Ratio Ch:IFN- γ :PGA	[IFN- γ] ng/ml	Particle size (nm)	Polydispersity	Zeta potential (mV)
Ch/ γ -PGA	1:0:1.5	0	295.0 \pm 12.7	0.28 \pm 0.01	18.1 \pm 0.7
	1:0.1:1.5	43	301.7 \pm 4.6	0.28 \pm 0.01	16.7 \pm 1.9
	1:0.25:1.5	107	301.2 \pm 9.1	0.27 \pm 0.01	18.3 \pm 0.4
Ch/IFN- γ / γ -PGA	1:0.35:1.5	150	315.6 \pm 8.9	0.28 \pm 0.01	18.6 \pm 1.4
	1:0.5:1.5	214	319.6 \pm 26.6	0.43 \pm 0.05	15.5 \pm 1.1
	1:0.7:1.5	300	855.7 \pm 47.5	0.66 \pm 0.03	-5.1 \pm 0.5

b.

