

Electronic Supplementary Material (ESI) for Biomaterials Science.
This journal is © The Royal Society of Chemistry 2019

Storage time ^a	Raw exosome (Raw exo)		Nanogel/Raw exo hybrid (1:1) ^c	
	Size $\pm$ S.D. (nm) ^b	ζ -potential $\pm$ S.D. (mV) ^b	Size $\pm$ S.D. (nm) ^b	ζ -potential $\pm$ S.D. (mV) ^b
0 h	157 $\pm$ 3	-11.9 $\pm$ 0.9	170 $\pm$ 11	-4.1 $\pm$ 0.8
4 h	162 $\pm$ 8	-11.0 $\pm$ 0.4	175 $\pm$ 10	-3.4 $\pm$ 1.1
24 h	156 $\pm$ 9	-12.1 $\pm$ 0.8	175 $\pm$ 12	-4.0 $\pm$ 0.5