

Supplementary Information

Electronic Structure, Ion Diffusion and Cation Doping in the $\text{Na}_4\text{VO}(\text{PO}_4)_2$ Compound as a Cathode Material for Na-ion Batteries

Pablo A. Aparicio^a and Nora H. de Leeuw^a

^a School of Chemistry, Cardiff University, Main Building Park Place, Cardiff CF10 3AT, United Kingdom

^b School of Chemistry, University of Leeds, Leeds LS2 9JT, United Kingdom

Email:

*apariciosanchezp@cardiff.ac.uk

*n.h.deleeuw@leeds.ac.uk

Table SII. Pedone interatomic potential parameters of NaVOPO_4 polymorphs.¹ The V-O parameters were optimized using the GULP software.²

Buckingham: $Ae^{-r/\rho} - Cr^{-6}$	A (eV)	ρ (Å)	C (eV Å⁶)	Cut-off (Å)
$\text{Na}^{0.6}\text{-O}^{-1.2}$	2010.33	0.261901	28.1687	$r_{\min} = 0.0/r_{\max} = 15.0$
$\text{P}^3\text{-O}^{-1.2}$	28357	0.178335	68.0998	$r_{\min} = 0.0/r_{\max} = 15.0$
$\text{V}^3\text{-O}^{-1.2}$	2306.19	0.228157	0	$r_{\min} = 0.0/r_{\max} = 15.0$
$\text{V}^{2.4}\text{-O}^{-1.2}$	2306.19	0.228157	0	$r_{\min} = 0.0/r_{\max} = 15.0$
$\text{O}^{-1.2}\text{-O}^{-1.2}$	2067.72	0.342846	214.2	$r_{\min} = 0.0/r_{\max} = 15.0$

Table SI2. Computed and experimental bond lengths of β -Na₄VO(PO₄)₂ compound (in Å).

β -Na ₄ VO(PO ₄) ₂		
	Comp.	Exp. ^a
V-O	1.749	1.845
	1.940	1.868
	1.966	1.945
	1.977	1.950
	1.989	1.967
	2.043	1.992

P-O	1.527	1.518
	1.542	1.519
	1.561	1.529
	1.564	1.615

Na(1)-O	2.297	2.260
	2.324	2.336
	2.394	2.431
	2.432	2.452
	2.433	2.478
	2.459	2.507
Na(2)-O	2.243	2.223
	2.247	2.234
	2.312	2.285
	2.329	2.414
	2.712	2.657
	2.816	2.853
Na(3)-O	2.271	2.309
	2.332	2.323
	2.372	2.369
	2.410	2.492
Na(4)-O	2.325	2.301
	2.460	2.489
	2.470	2.536
	2.517	2.600
	2.617	2.623
	2.624	2.698

^a Ref. ³.




Figure S11. Mean square displacement (MSD) vs. time for the $\text{Na}_4\text{VO}(\text{PO}_4)_2$ compound at 300 and 600 K.

References

- 1 A. Pedone, G. Malavasi, M. C. Menziani, A. N. Cormack and U. Segre, *J. Phys. Chem. B*, 2006, **110**, 11780–11795.
- 2 J. D. Gale and A. L. Rohl, *Mol. Simul.*, 2003, **29**, 291–341.
- 3 J. Kim, H. Kim and S. Lee, *Chem. Mater.*, 2017, **29**, 3363–3366.