

Electronic Supplementary Information:

Direct electrospinning of titania nanofibers with ethanol

Brian S. Chapman, Sumeet R. Mishra and Joseph B. Tracy*

Department of Materials Science and Engineering, North Carolina State University, Raleigh,
North Carolina 27695, USA

Supplementary Figures




Figure S1. Scanning electron microscopy images with a common scale bar of the products of electrospray and electrospinning of a TiO_2 sol, prepared in a different batch than the results reported in the main text, at a flow rate of $0.6 \mu\text{L}/\text{min}$. Variation of the applied voltage and tip-collector distance allows optimization of electrospinning, which was at 10 kV and 14 cm for this sample.