

Supporting Information

A triple-triangle cluster derived from a simple tridentate ligand

Takuya Shiga,^{*a} Natsumi Okawa^a and Hiroki Oshio^{a,b}

- a. Graduate School of Pure and Applied Sciences, University of Tsukuba, Tennodai 1-1-1, Tsukuba, Ibaraki 305-8571, Japan.
- b. State Key Laboratory of Fine Chemicals, Dalian University of Technology
2 Linggong Rd., 116024 Dalian, China

Corresponding author

Dr. Takuya Shiga

Graduate School of Pure and Applied Sciences,

University of Tsukuba

Tennodai 1-1-1, Tsukuba, Ibaraki 305-8571 (Japan)

TEL: (+81)29-852-5923

FAX: (+81)29-852-4426

E-mail: shiga@chem.tsukuba.ac.jp

Experimental Procedures

The multidentate ligand H₂L (2,6-bis(1,5-diphenyl-1*H*-pyrazole-3-yl)pyridine) was synthesized the previously reported synthetic method.¹

Elemental analyses for carbon, hydrogen, and nitrogen were performed with a PerkinElmer CHN analyzer (Model 2400). The IR spectra (KBr pellets, 4000-400 cm⁻¹) were recorded by using a Shimadzu Model IR Affinity-1 spectrometer. The magnetic data were obtained with a Quantum Design MPMS 5XL superconducting quantum interface device (SQUID) susceptometer. The magnetic susceptibility measurements were performed in the 1.8 - 300 K temperature range under a 0.05 T dc applied magnetic field. Diamagnetic corrections were applied using Pascal's constants. Variable-temperature Mössbauer experiments were carried out using a ⁵⁷Co/Rh source in a constant acceleration transmission spectrometer (Topologic Systems) equipped with an Iwatani HE05/CW404 Cryostat. The spectra were recorded at 20 K. The spectrometer was calibrated using standard α -Fe foil.

Data collections for single crystal X-ray diffraction for **1** were performed on a Bruker SMART APEX II, with a CCD area detector with graphite monochromated Mo-K α ($\lambda = 0.71073$ Å) radiation. The structure was solved by direct methods and refined by full-matrix least-squares methods based on F^2 using the SHELXL software. Non-hydrogen atoms were refined anisotropically. All hydrogen atoms were positioned geometrically and refined with isotropic displacement parameters according to the riding model. All geometrical calculations were performed using the SHELXL software. Data sets for **1** were treated with the SQUEEZE program from the PLATON suite to remove highly disordered solvent molecules from the calculations.




Figure S1 π - π stacking interactions of **1**. Phenyl rings were omitted for clarity. Blue dotted lines represent π - π stacking interactions.

References

- 1 Y. Zhou, W. Chem and D. Wang, *Dalton Trans.*, 2008, 1444.