

N-Doped Porous Tremella-Like Fe₃C/C Electrocatalysts Derived from Metal-Organic Frameworks for Oxygen Reduction Reaction

Xinxin Yang,^a Xiang Sun,^a Muhammad Rauf,^a Hongwei Mi,^a Lingna Sun,^a Libo

Deng,^a Xiangzhong Ren,^a Peixin Zhang,^{a,b} Yongliang Li^{a,b*}

^a College of Chemistry and Environmental Engineering, Shenzhen University, Shenzhen, Guangdong, 518060, P.R. China

^b Guangdong Flexible Wearable Energy Tools Engineering Technology Research Centre, Shenzhen University, Shenzhen, Guangdong, 518060, P.R. China

* Corresponding author: Yongliang Li, E-mail: liyli@szu.edu.cn, Tel/Fax: +86-755-26931162




Figure S1: XPS spectra of N1s for (a) NPM-0, (b) NPM-0.02, (c) NPM-0.04, (d) NPM-0.08.




Figure S2: The content of different types of nitrogen in XPS N 1S for NPM-0, NPM-0.02, NPM-0.04, and NPM-0.08 electrocatalysts.

Table S1 Percentage of different types of nitrogen in XPS N1s for NPM-0, NPM-0.02, NPM-0.04, NPM-0.08 electrocatalysts.

Sample	Pyridinic-N	Metal-N	Pyrolic-N	Graphitic-N	Oxidized -N
NPM-0	54.7 %	/	8.7 %	30.9 %	5.7 %
NPM-0.02	43.8 %	10.9 %	7 %	28.8 %	9.5 %
NPM-0.04	17.6 %	21.3 %	13.9 %	33.3 %	13.9 %
NPM-0.08	11.7 %	16.8 %	42.3 %	21.9 %	7.3 %