

Supporting information

Specification of SBA-15 and MDA-SBA-15 mesoporous silica from N₂ adsorption-desorption isotherms.

Sample	D _{BJH} (nm)	S _{BET} (m ² /g)	V _{Total} (ml/g)
SBA-15	7.0	604	1.70
MDA-SBA-15	4.7	293	0.93