Electronic Supplementary Information (ESI)

## Preparation and characterization of a supramolecular hydrogel made of phospholipids and oleic acid with a high water content

Kirian Talló\*<sup>a</sup>, Manel Bosch<sup>b,c</sup>, Ramon Pons<sup>a</sup>, Mercedes Cocera<sup>d</sup> and Olga López<sup>a</sup>

## Results and discussion



Fig. S1 Effect of the pH on the hydrogel formation. From left to right the pH is 9, 6.5 and 4 respectively. As it can be seen, the hydrogel is only formed at pH 6.5

## Captions for Video S1 and S2

Video S1: Volume rendering and stack animation from confocal microscopy images of the hydrogel acquired with a 63X objective.

Video S2: Stack animation from confocal microscopy images of the hydrogel obtained with a 63X objective and zoom x3 function.

<sup>&</sup>lt;sup>a</sup> Department of Surfactants and Nanobiotechnology, Institute of Advanced Chemistry of Catalonia (IQAC-CSIC), C/Jordi Girona 18-26, 08034, Barcelona, Spain.

<sup>&</sup>lt;sup>b</sup> Advanced Optical Microscopy Unit, Scientific and Technological Centers of the Universitat de Barcelona (CCiTUB), Barcelona, 08028, Spain.

<sup>&</sup>lt;sup>c</sup> Department of Biochemistry and Molecular Biomedicine, Faculty of Biology, Universitat de Barcelona, 08028, Spain.

<sup>&</sup>lt;sup>d.</sup>Bicosome S.L., C/Jordi Girona 18-26, 08034, Barcelona, Spain.