

Superhydrophobic TiO₂ Nano-strawberry Films Fabricated at Low Temperature and the Reversible Switch

Wentao Sun^a, Shuyun Zhou^b, Ping Chen^{*b} and Lianmao Peng^a

*Correspondence to Ping Chen, chenlab@mail.ipc.ac.cn

a Key Laboratory for the Physics and Chemistry of Nanodevices and Department of Electronics, Peking University, Beijing 100871, P.R. China.

b Technical Institute of Physics and Chemistry, Chinese Academy of Sciences, Beijing 100080, P. R. China.

Supporting Information

The advanced/receding contact angle (CA), contact angle hysteresis, and sliding angle of the superhydrophobic TiO₂ film.

Advanced CA	169.7°
Receding CA	158.4°
CA hysteresis	11.3°
Sliding angle	13°