

Hybrid silica nanotubes with chiral walls

Yuanli Chen,^a Baozong Li,^a Xiaojian Wu,^a Xiulin Zhu,^a Masahiro Suzuki,^b Kenji Hanabusa^b and Yonggang Yang^{a*}

^aKey Laboratory of Organic Synthesis of Jiangsu Province, College of Chemistry and Chemical Engineering, Suzhou University, Suzhou 215123, P.R. China. ^bDepartment of Functional Polymer Science, Faculty of Textile Science and Technology, Shinshu University, Ueda 386-8567, Japan

E-mail: ygyang@suda.edu.cn




Figure S1. FESEM (a) and TEM (b) images of left-handedly coiled tubular ribbons and tube-in-tube structures.




Figure S2. TEM images of the reaction mixture at different reaction time. (a) 45 s and (b) 90 s (Preparation condition: 20 mg of **12K**, 2.2 mL of H₂O, 1.8 mL of EtOH, 40 mg of TMAPS); (c) 180 s and (d) 460 s (Preparation condition: 20 mg of **12K**, 2.2 mL of H₂O, 1.8 mL of EtOH, 10 mg of 1-propylamine, and 30 mg of BTEB). Scale bar length: (a) and (b) are 0.2 μm; (c) and (d) are 1.0 μm.