

Supplementary Information

Two-Photon Fluorescent Microporous Bithiophene Polymer *via Suzuki Cross-Coupling*

Debao Xiao,^{*a,b} Yan Li,^a Lili Liu,^a Bin Wen,^b
Zhanjun Gu,^c Chuang Zhang^d and Yongsheng Zhao^d


^aHebei Key Laboratory of Applied Chemistry, School of Environmental and Chemical Engineering,
Yanshan University, Qinhuangdao 066004, China,

^bState Key Laboratory of Metastable Materials Science and Technology (MMST),
Yanshan University, Qinhuangdao 066004, China


^cKey Laboratory for Biomedical Effects of Nanomaterials and Nanosafety, Institute of High Energy Physics,
Chinese Academy of Sciences, Beijing 100049, China

^dInstitute of Photochemistry, Institute of Chemistry, Chinese Academy of Sciences, Beijing 100190

E-mail: debao.xiao@ysu.edu.cn



(A)



(B)

Element	Weight%	Atomic%
C K	69.67	82.92
O K	4.53	4.04
Al K	0.63	0.33
Si K	23.45	11.93
S K	1.73	0.77
Totals	100.00	

(C)

Figure S1. EDX analysis results (A) SEM image of the sample section for EDX analysis, (B) EDX spectrum, and (C) calculation result.




Figure S2. Thermogravimetric analysis (TGA-DTA) curves for the as-obtained polymer MBP recorded under an argon atmosphere with a heating rate of 10 °C/Min.




Figure S3. (A) Nitrogen adsorption isotherm curve (a) and desorption curve (b) measured at 77K, and (B) Pore size distribution curve.