

Electronic Supplementary Information

for

The thermally stable helical chain and octanuclear Ag(I) coordination networks with yellow luminescences

Chunfeng Yan^{a, b}, Lian Chen^a, Rui Feng^{a, b}, Feilong Jiang^{*a}, Maochun Hong^{*a}

^aKey Laboratory of Optoelectronic Materials Chemistry and Physics, Fujian Institute of Research on the Structure of Matter, Chinese Academy of Sciences, Fuzhou 350002, China

^bGraduate school of Chinese Academy of Science, Beijing, China

Fax: +86-59 -83714605; Tel: +86-59-83714605

E-mail: fjiang@fjirsm.ac.cn; hmc@fjirsm.ac.cn




Fig. S1. Emission spectra of free tpt at room temperature and 10 K in crystal-state.

Table S1 Photoluminescent Lifetime Data for Complexes **1** and **3**

Complex	Lifetime (ms)		
	τ_1	τ_2	τ_3
1	11.93 (46.73%)	2.486 (10.90%)	29.99 (42.37%)
3	2.282 (14.46%)	9.384 (42.27%)	35.34 (43.27%)