

Electronic Supplementary Information (ESI)

Table 1 experimental details for samples **S1-S10**.

	Urea (mol)	Zn(NO <sub>3</sub> ) <sub>2</sub> (mol)	Annealing temperature (°C)
<b>S1</b>	0.002	0.002	As prepared
<b>S2</b>	0.006	0.002	As prepared
<b>S3</b>	0.015	0.002	As prepared
<b>S4</b>	0.02	0.002	As prepared
<b>S5</b>	0.02	0.002	300
<b>S6</b>	0.02	0.002	400
<b>S7</b>	0.02	0.002	500
<b>S8</b>	0.006	0.002	300
<b>S9</b>	0.006	0.002	400
<b>S10</b>	0.006	0.002	500