

Supplementary Information

Growth, Thermal and Optical Properties of a Novel Nonlinear Optical Material $\text{K}_3\text{B}_6\text{O}_{10}\text{Cl}$

Hongping Wu,^{a,b} Shilie Pan,^{a*} Hongwei Yu,^a Dianzeng Jia,^b Aiming Chang,^a Hongyi Li,^a Fangfang Zhang,^a Xia Huang^a

Figure S1. KBOC crystal grown by the top-seeded growth method. (a) The temperature was reduced at a rate of 0.2 °C/day. (b) The temperature was reduced at a rate of 1 °C/day. (The minimum scale of the ruler is one millimeter.)

