

Ferromagnetic intermolecular exchange interaction in ethynyl-verdazyl radical crystals

Areej Merhi,^a Thierry Roisnel,^a Stéphane Rigaut,^a Cyrille Train^b and Lucie Norel^{a*}

(a) UMR 6226 CNRS - Université de Rennes 1, Institut des Sciences Chimiques de Rennes, Campus de Beaulieu, F-35042 Rennes Cedex. Fax: +33 2 23 23 69 39; E-mail: lucie.norel@univ-rennes1.fr

(b) LNCMI, UPR 3228, CNRS-UJF-UPS-INSA and UJF, 38042 Grenoble, France

Supporting Information

Table of Contents

Figure S1 : UV-vis absorption spectrum for **2** in dichloromethane.

Figure S2 : Powder X-ray diffraction patterns of radical **2**




Figure S1 : UV-vis absorption spectrum for **2** in dichloromethane.




Figure S2 : Powder X-ray diffraction patterns of radical **2** at room temperature : red points are observed pattern and black line is refined profile with FullProf program in profile matching mode. Vertical ticks are refined Bragg peak positions in P-1 triclinic space group with $a = 4.0642(1)$, $b = 11.1503(3)$, $c = 12.8947(3)$ Å, $\alpha = 104.742(1)$, $\beta = 94.342(32)$, $\gamma = 94.131(2)^\circ$.