


Electro-oxidation of formic acid catalyzed by FePt nanoparticles

Wei Chen,[†] Jaemin Kim,[‡] Shouheng Sun,[‡] and Shaowei Chen^{†*}

1. TEM image of the FePt nanoparticles

TEM image of 3 nm Fe₂₀Pt₈₀ nanoparticles. The sample was prepared by drying a hexane dispersion of the particles on an amorphous carbon-coated copper grid. The particles were imaged using a Philips TEM 420 (120 KV).



* Corresponding author.
Tel: 831-459-5841;
Fax: 831-459-2935;
E-mail: schen@chemistry.ucsc.edu

2. XRD Pattern of the FePt nanoparticles

X-ray diffraction pattern of the FePt nanoparticle assembly on a glass substrate. The pattern was collected on a Bruker AXS D8 Advance diffractometer under Cu $K\alpha$ radiation ($\lambda = 1.5405\text{\AA}$).

